

>110 psi High Density NH Polyiso Cover Board



EnergyGuard™ **GAF** NHHDPPlus Polyiso Cover Board



Description:

EnergyGuard™ NH HD Plus Polyiso Cover Board is made of a durable coated glass fiber facer (CGF) bonded to a core of high density non-halogenated polyisocyanurate foam designed to be used as a cover board for low-slope roof systems.

Features and Benefits:

- EnergyGuard™ NH HD Plus Polyiso Cover Board is better for the environment because it does not contain potentially hazardous flame-retardant chemicals
- EnergyGuard™ NH HD Plus Polyiso Cover Board holds a Health Product Declaration (HPD), is Green Circle third party recycled content certified and is a Red List Free product with a Declare label designation
- R-value 2.5. Highest R-value compared to non-polyiso cover boards of equivalent thickness
- High compressive strength 110 psi (758 kPa) minimum up to 139 psi (958 kPa) maximum
- Light weight - only 13 lbs (5.9kg) per 4' x 8' (1.22m x 2.44m) board, easy to cut, easy to install
- Meets the requirements of D3273 for resistance to mold growth ††
- Excellent dimensional stability, high moisture resistance and low water permeability
- Idea for Low-Slope roofs with high foot traffic, hail events and metal retrofit applications*

Panel Characteristics:

- Available in 1/2" (12.7mm) thickness
- Available in 4' x 4' (1.22m x 1.22m) and 4' x 8' (1.22m x 2.44m)
- 48 pieces per bundle

Codes & Compliance:

- Meets the requirements of ASTM C1289, Type II, Class 4, Grade 2
- FM Approved, including as a component of a Class 1-SH hail rated assembly. Refer to ROOFNav.com for specific assemblies
- Classified by UL in accordance with ANSI/UL 790, ASTM E1256. Refer to UL Product iQ for specific assemblies
- Miami Dade County Product Control Approved
- State of Florida Approved
- For additional information, contact GAF at 877-423-7663 or designservices@gaf.com



Sustainability:

- EnergyGuard™ NH HD Plus Polyiso Cover Board holds the polyiso industry's only specific Environmental Product Declaration (EPD) for non-halogenated products
- Sustainable design projects pursuing certifications under a green building rating system such as LEED v4, or Living Building Challenge will benefit from these certifications and listings
- Manufactured with EPA-compliant blowing agents containing no CFCs or HCFCs; has zero ozone depletion potential (ODP) and negligible global warming potential (GWP)
- Green Circle Certified for recycled content
- Potential LEED Credits for polyiso use
- Health Product Declaration (HPD)
- Living Building Challenge Red List Approved
- GREENGUARD Gold
- Where sold compliant with State HFC regulations. More information available at www.polyiso.org

For more information go to gaf.com/green

Declare.



Visit gaf.com

We protect what matters most™



Typical Physical Property Data

PROPERTY	TEST METHOD	VALUES
Compressive Strength	ASTM D1621	110 psi min (758 kPa) up to 139 psi max (958 kPa)
Dimensional Stability Change (<i>length + width</i>)**	ASTM D2126	< 1% linear change
Flute Spanability	ASTM E661	4.75" (102.7mm)
Flexural Strength	ASTM C203	400 psi min (2,750 kPa)
Tensile Strength	ASTM C209	2000 psf min (95 kPa)
Water Absorption (<i>percent by volume</i>)	ASTM C209	4% max
Water Vapor Permeance	ASTM E96, Procedure A	2.0 perm max (85.8ng/Pa•s•m ²)
Service Temperature †		260°F (126.7°C) or less
Resistance to Mold ††	ASTM D3273	Pass (10)
R-Value	ASTM C518	2.5

* GAF warranties and guarantees do not provide coverage against traffic except where GAF walkways are applied. Refer to GAF.com for more information on warranty and guarantee coverage and restrictions.

* GAF warranties and guarantees do not provide coverage against hail except where additional puncture resistance coverage is purchased on eligible jobs. Refer to GAF.com for more information on warranty and guarantee coverage and restrictions.

* Please see applicable manual for retrofit installations.

** Stated dimensional stability tolerance: thickness shall not diminish by more than 4% max (at -40° F or 200° F at ambient RH) or by more than 4.5% max (158° F & 97% RH).

† These numerical ratings are not intended to reflect hazards presented by these or any other material under actual fire conditions.

†† GAF warranties and guarantees do not provide coverage against mold or other biological growth. Refer to gaf.com for more information on warranty and guarantee coverage and restrictions.

Warnings and Limitations

- EnergyGuard™ NH HD Plus Polyiso Cover Board is a non-structural, non load-bearing material. It is not designed for direct traffic usage unless adequately protected.
- EnergyGuard™ NH HD Plus Polyiso Cover Board should be stored protected from the elements. Bundle wrap is not for use as waterproofing for boards. No more insulation should be installed than can be completely covered with roofing on the same day.
- As unprotected polyisocyanurate will burn, fire safety precautions should be observed wherever insulation products are used.
- Direct mopping of modified bitumen roofing or built-up roofing (BUR) to EnergyGuard™ NH HD Plus Polyiso Cover Board is not approved.
- Refer to PIMA Technical Bulletin No. 109 Storage and Handling Recommendations for Polyiso Roof Insulation at www.polyiso.org
- Refer to the application specifications in the current membrane manufacturer's application and specifications manual for proper installation procedures.



Visit gaf.com

We protect what matters most™

